



TITLE:

# Laboratory of Dielectrics (Special Issue on the Commemoration of the Fiftieth Anniversary)

AUTHOR(S):

---

CITATION:

Laboratory of Dielectrics (Special Issue on the Commemoration of the Fiftieth Anniversary). Bulletin of the Institute for Chemical Research, Kyoto University 1977, 54(6): 390-395

ISSUE DATE:

1977-03-25

URL:

<http://hdl.handle.net/2433/76702>

RIGHT:

## LABORATORY OF DIELECTRICS

Head: Dr. Naokazu Koizumi

This laboratory deals with basic research and applications of dielectrics. The subjects of researches which have been conducted for recent ten years are as in the following: (1) dielectric polarization and relaxation of polar liquids; (2) dielectric relaxations and molecular motions in polymers; (3) dielectric properties of heterogeneous systems; (4) dielectric approach to biological suspensions; (5) data analysis and technique in dielectric measurements.

### 1. Dielectric Polarization and Relaxation of Polar Liquids

Dielectric behavior of polar liquids has been studied for some diols, ethanolamines, and ethylenediamine oligomers. Dielectric relaxations in 2-methyl 2,4-pentanediol, 2-ethyl 1,3-hexanediol, dipropylene glycol at low temperatures were fitted by the Davidson-Cole relaxation characteristic of strongly hydrogen-bonded liquids. Introduction of the amino group into molecules reduces the intermolecular hydrogen bonding. This effect was confirmed with the Kirkwood correlation factor evaluated from the dielectric constants of ethanolamines and ethylenediamine oligomers. Relaxations found for those molecules having the amino group as aminoethyl ethanolamine, diethylenetriamine *etc.* were not expressed by the Davidson-Cole relaxation, but interpreted as superposition of the Cole-Cole and the Davidson-Cole relaxations. The equilibrium dielectric constant of these hydrogen-bonded liquids varied linearly with the reciprocal of the thermodynamic temperature.

### 2. Dielectric Relaxations and Molecular Motions in Polymers

Dielectric behavior of a variety of fluorocarbon polymers has been investigated over wide ranges of frequency and temperature and discussed in terms of molecular motions and other physical properties.

Precision measurements of poly(tetrafluoroethylene) PTFE were carried out over a frequency range of 10 Hz to 300 kHz at temperatures of  $-195$  to  $170^{\circ}\text{C}$ . The dielectric constant of PTFE was about 2 over the entire range of frequency studied, being slightly dependent on the degree of crystallinity and temperature. The dielectric constant showed an abrupt change at the crystalline transition of  $19^{\circ}\text{C}$  in highly crystalline PTFE. The dielectric loss was very low, showing a small loss peak of the  $\gamma$  relaxation near  $-80^{\circ}\text{C}$  at 1 kHz. Copolymers of tetrafluoroethylene and hexafluoropropylene, FEP, are also non-polar polymers. FEP, however, exhibited three small loss peaks,  $\alpha$ ,  $\beta$ , and  $\gamma$ , which appeared near  $100$ ,  $-50$ , and  $-170^{\circ}\text{C}$  at 1 kHz, respectively. The glass transition was found at  $60^{\circ}\text{C}$ . The  $\alpha$  and  $\beta$  relaxations were assigned to micro-Brownian motions of backbone chains and local motions of short

molecular segments, respectively. Poly(vinylidene fluoride) PVDF showed three relaxations, the  $\alpha$  relaxation near 130°C, the  $\beta$  near 0°C, and the  $\gamma$  near -30°C at 100 kHz. In the  $\alpha$  relaxation the loss peak and the relaxation time increased not only with increasing lamellar thickness but also with crystal defects in crystalline regions. This relaxation was attributed to molecular motions in crystalline regions. The  $\beta$  relaxation was ascribed to conformational rearrangements of backbone molecular chains. Effects of orientation of molecular chains by drawing were reflected on dielectric relaxations of PVDF. Dielectric behavior of another copolymer has been studied for copolymers of vinylidene fluoride VDF and hexafluoropropylene HFP with different comonomer contents. A copolymer with low HFP contents showed the  $\alpha$  relaxation similar to that in PVDF. Copolymers with high HFP contents were amorphous, showing relaxations associated with conformational rearrangements of molecular chains and local motions of molecules below the glass transition.

### 3 Dielectric Properties of Heterogeneous Systems

As the integral parts of dielectric approaches to colloidal disperse systems, a number of dielectric investigations have been carried out on diphasic systems such as emulsions in oil-in-water and water-in-oil types theoretically as well as experimentally.

On the basis of the Wagner theory of the interfacial polarization, a new theory was developed which is expected to be applicable to spherical disperse systems in higher concentrations. The dielectric behavior observed for the oil-in-water emulsions was understood quantitatively with this new theory. Striking dielectric relaxations were observed for the water-in-oil emulsions in accordance with the theoretical prediction. The data on the dielectric relaxations were in satisfactory agreement with the new theory for the preparations by the minimal use of emulsifiers.

Most examples of emulsions reported so far are of a diphasic system in which the conductivities of the constituent phases are several orders of magnitude different from each other. In this instance the approximate expressions of the theory were put to use on application of the theories to the experimental results. For general cases of diphasic systems where the approximation is not allowable, new procedure is being developed for practical use of the Wagner and the new theory.

Dielectric measurements were made on  $\text{Fe}_3\text{O}_4$  and some ferrites in fine powders precipitated from aqueous solutions and in calcined powders. In the temperature range from 77 to 300 K some ferrites containing  $\text{Fe}^{2+}$  ions showed dielectric relaxations, which were interpreted as interfacial polarization due to the heterogeneous structure of the oxides. Another type of dielectric relaxations was observed for the same ferrites at temperatures from 77 to 4.2 K. This kind of dielectric relaxation was considered to be caused by the hopping of electrons between  $\text{Fe}^{2+}$  and  $\text{Fe}^{3+}$  ions. Magnetic relaxations in the same ferrites were also investigated.

As further extension of the dielectric approaches to the spherical disperse systems, a triphasic system consisting of conducting spheres covered with an insulating shell phase and dispersed in a conducting medium was investigated in connection with an

analysis of biological suspensions. On the basis of a theoretical expression proposed by Pauly and Schwan for a suspension of shell-spheres, fitting procedure was established so that the dielectric constants and the conductivities of the inner spheres and of the shell phase may be determined by means of the fittings of the theoretical curves to dielectric relaxation data observed.

#### 4 Dielectric Approach to Biological Suspensions

The curve-fitting method established was successfully applied to some biological suspensions to obtain the dielectric constants and the conductivities of the inner phase and of the shell phase of the suspending particles from the dielectric relaxation data observed.

It was found for the synaptosome suspensions that the conductivity of the synaptosome interior was about 37% of the outer medium conductivity irrespective of the salt concentration of the outer medium, and that the dielectric constant for the inner phase was about 35. The membrane capacitance was estimated to be  $0.7 \mu\text{F cm}^{-2}$ , remaining constant irrespective of species and concentration of the univalent salts examined.

Dielectric measurements were made on suspensions of intact yeast cells. The suspensions showed typical dielectric relaxations which are caused by the triphasic structure with the cytoplasm, the cell membrane, and the suspending medium. The dielectric relaxation data were subjected to the analysis by the curve-fitting method to deduce the characteristics of the cytoplasm and the cell membrane. The cell membrane capacitance was estimated to be  $1.1 \mu\text{F cm}^{-1}$ . The conductivity of the cytoplasm was almost unchanged with varying salt concentrations of the suspending medium. The dielectric constant of the cytoplasm was estimated to be about 50. The effect of some surfactants on the yeast cell membranes was also examined in connection with bactericidal effect.

#### 5 Data Analysis and Technique in Dielectric Measurements

The expressions of the complex capacitance and conductance were derived for the Cole-Cole relaxation. Numerical values of the normalized complex capacitance and conductance were tabulated as a function of frequency over a wide range of the distribution parameter of relaxation times to facilitate the numerical analysis of relaxation as observed in the frequency domain technique.

The theory of a transient current method in dielectric measurements has been discussed in connection with investigation of relaxation processes using the time domain technique. Numerical values of the response functions and their integrals in the Debye, Cole-Cole, and Davidson-Cole types of relaxation were compiled over a wide range of the distribution parameter of relaxation times. These data were intended for investigation of relaxation as observed with a transient current method using either step or ramp voltage. In connection with the transient current method the accuracy of the Hamon approximation for evaluating the dielectric loss and the relaxation time was examined with regard to the Cole-Cole, Davidson-Cole, and Williams-Watts relaxations. It was found that the approximation is applicable, with fairly good

accuracy, only to the Cole-Cole relaxation with a broad distribution of relaxation times.

An ultra low-frequency bridge which is usable in a frequency range of 1 mHz to 100 Hz was built for dielectric measurements of slow relaxation processes in polymer solids. The bridge was featured with three-terminal measurements and with capability of the distinction between the capacitive and conductive unbalances in the null detection at low frequencies. The time required for the final balance was greatly reduced in this bridge.

## Publications

(\*indicates an article published in Japanese)

### Originals

1. T. Hanai, D. A. Haydon, and J. Taylor: The Thickness and Electrical Properties of Black Hydrocarbon Films in Aqueous Solutions, *Kolloid Z*, **195**, 41 (1964).
2. T. Hanai, D. A. Haydon, and J. Taylor: An Investigation by Electrical Methods of Lecithin-in-Hydrocarbon Films in Aqueous Solutions, *Proc. Roy. Soc.*, **A281**, 377 (1964).
3. T. Hanai, D. A. Haydon, and J. Taylor: Some Further Experiments on Bimolecular Lipid Membranes, *J. Gen. Physiol.*, **48**, 59 (1965).
4. T. Hanai, D. A. Haydon, and J. Taylor: Polar Group Orientation and the Electrical Properties of Lecithin Bimolecular Leaflets, *J. Theoret. Biol.*, **9**, 278 (1965).
5. T. Hanai, D. A. Haydon, and J. Taylor: The Influence of Lipid Composition and of Some Adsorbed Proteins on the Capacitance of Black Hydrocarbon Membranes, *ibid.*, **9**, 422 (1965).
6. T. Hanai, D. A. Haydon, and J. Taylor: The Variation on Capacitance and Conductance of Bimolecular Lipid Membranes with Area, *ibid.*, **9**, 433 (1965).
7. T. Hanai, D. A. Haydon, and W. R. Redwood: The Water Permeability of Artificial Bimolecular Leaflets: A Comparison of Radio-Tracer and Osmotic Methods, *Ann. N. Y. Acad. Sci.*, **137**, 731 (1966).
8. T. Hanai and D. A. Haydon: The Permeability to Water of Bimolecular Lipid Membranes, *J. Theoret. Biol.*, **11**, 370 (1966).
9. N. Koizumi, S. Yano, F. Tsuji, N. Nakamura, and S. Kobayashi: Dielectric Properties of Gamma-Irradiated Tetrafluoroethylene-Hexafluoropropylene Copolymers, *Bull. Inst. Chem. Res., Kyoto Univ.*, **45**, 97 (1967).
10. T. Hanai and N. Koizumi: Dielectric Properties of Water-Oil System Solubilized with Aerosol OT, *ibid.*, **45**, 342 (1967).
11. E. Ikada: Dielectric Behavior of Ethylenediamine Oligomer, *ibid.*, **45**, 352 (1967).
12. N. Koizumi, K. Tsunashima, and S. Yano: Dielectric Relaxation in Copolymers of Vinylidene Fluoride and Hexafluoropropylene, *J. Polym. Sci. B*, **7**, 815 (1967).
13. N. Koizumi, S. Yano, and F. Tsuji: Dielectric Properties of Polytetrafluoroethylene and Tetrafluoroethylene-Hexafluoropropylene Copolymer, *ibid.*, **C**, **23**, 499 (1968).
14. N. Koizumi, S. Yano, K. Tsunashima, and F. Tsuji: Dielectric Relaxation in Gamma-Irradiated Tetrafluoroethylene-Hexafluoropropylene Copolymers at Low Temperatures, *Bull. Inst. Chem. Res., Kyoto Univ.*, **46**, 30 (1968).
15. E. Ikada, Y. Hida, H. Okamoto, J. Hagino, and N. Koizumi: Dielectric Properties of Ethanolamines, *ibid.*, **46**, 239 (1968).
16. N. Koizumi and S. Yano: Three-Terminal Dielectric Cell for Solids, *ibid.*, **47**, 320 (1969).
17. T. Hanai, M. Kajiyama, S. Morita, and N. Koizumi: Some Properties of Black Lipid Membranes Formed from Lipids Extracted from Egg Yolk, *ibid.*, **47**, 327 (1969).
18. N. Koizumi, S. Yano, and K. Tsunashima: Dielectric Relaxation of Poly(Vinylidene Fluoride), *J. Polym. Sci. B*, **7**, 59 (1969).
19. S. Yano: Dielectric Relaxation and Molecular Motion in Poly(Vinylidene Fluoride), *ibid.*, **A-2**, **8**, 1057 (1970).

20. T. Hanai, S. Morita, N. Koizumi, and M. Kajiyama: The Formation and Properties of Bilayers Containing Lipids Extracted from Bovine Erythrocytes, *Bull. Inst. Chem. Res., Kyoto Univ.*, **48**, 147 (1970).
21. K. Iwauchi, S. Yamamoto, Y. Bando, and N. Koizumi: Dielectric Properties of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>, *ibid.*, **48**, 159 (1970).
22. K. Iwauchi, S. Yamamoto, Y. Bando, T. Hanai, N. Koizumi, T. Takada, and S. Fukushima: Dielectric Properties of the Mixtures of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>, TiO<sub>2</sub> and Fe<sub>2</sub>TiO<sub>5</sub>, *Japan. J. Appl. Phys.*, **10**, 1513 (1971).
23. K. Iwauchi: Dielectric Properties of Fine Particles of Fe<sub>3</sub>O<sub>4</sub> and Some Ferrites, *ibid.*, **10**, 1520 (1971).
24. E. Ikada: Dielectric Properties of Some Diols, *J. Phys., Chem.*, **75**, 1240 (1971).
25. N. Koizumi, T. Hanai, and E. Ikada: Numerical Data of Complex Capacitance and Conductance for the Circular Arc Rule in Dielectric Relaxations, *Bull. Inst. Chem. Res., Kyoto Univ.*, **49**, 268 (1971).
26. Y. Kita, N. Koizumi and K. Maruyama: The Reaction of Nitrosobenzene with Benzylamine in Non-Aqueous Media, *ibid.*, **50**, 337 (1972).
27. N. Koizumi and Y. Kita: Numerical Tables of Response Functions and Their Integrals for Debye, Cole-Cole, and Davidson-Cole types of Dielectric Relaxation, *ibid.*, **50**, 499 (1972).
28. K. Asami, A. Irimajiri, T. Hanai, and N. Koizumi: A Method for Estimating Residual Inductance in High Frequency A. C. Measurements, *ibid.*, **51**, 231 (1973).
29. A. Irimajiri, K. Kamino, N. Uyesaka, A. Inouye, and T. Hanai: Electrical Properties of Synaptosome Vesicles, *J. Physiol. Soc. Japan*, **35**, 381 (1973).
30. T. Hanai: The Comparison of Permeation Properties to Materials of Biological Cell Membranes and Artificial Films, *Kagaku Koogaku*, **38**, 413 (1974).\*
31. S. Yano, K. Tadano, K. Aoki, and N. Koizumi: Alternating-Current Ionic Conduction and Dielectric Relaxation of Poly (Vinylidene Fluoride) at High Temperatures, *J. Polymer Sci., Part A-2*, **12**, 1875 (1974).
32. J. Crossley and N. Koizumi: Dielectric Relaxation of Some Aliphatic Esters in Cyclohexane Solution, *J. Chem. Phys.*, **60**, 4800 (1974).
33. K. Iwauchi, M. Kiyama, N. Koizumi, and Y. Bando: On the Dielectric Relaxation in Ferrites Due to Electron Hopping at Low Temperatures, *Bull. Inst. Chem. Res., Kyoto Univ.*, **52**, 596 (1974).
34. Y. Kita and N. Koizumi: Remarks on the Hamon Approximation, *Advan. Mol. Relaxation Processes*, **7**, 13 (1975).
35. M. Takagi, K. Asami, T. Hanai, and U. Kishimoto: Effect of Illumination on the Squid Rhodopsin Membrane at Oil-Water Interface, *Science Reports, College of General Education, Osaka Univ.*, **24**, 69 (1975).
36. A. Irimajiri, T. Hanai, and A. Inouye: Dielectric Properties of Synaptosomes Isolated from Rat Brain Cortex, *Biophys. Struct. Mechanism*, **1**, 273 (1975).
37. T. Hanai, N. Koizumi, and A. Irimajiri: A Method for Determining the Dielectric Constant and the Conductivity of Membrane-Bounded Particles of Biological Relevance, *ibid.*, **1**, 285 (1975).
38. A. Irimajiri, T. Hanai, and A. Inouye: Evaluation of a Conductometric Method to Determine the Volume Fraction of the Suspensions of Biomembrane-Bounded Particles, *Experientia*, **31**, 1373 (1975).
39. T. Hanai and N. Koizumi: Dielectric Relaxation of W/O Emulsions in Particular Reference to Theories of Interfacial Polarization, *Bull. Inst. Chem. Res., Kyoto Univ.*, **53**, 153 (1975).
40. S. Morita and T. Hanai: Spot Test Method Convenient for Detecting the Lipid Content in Column Chromatography, *ibid.*, **53**, 279 (1975).
41. K. Asami, T. Hanai, and N. Koizumi: Dielectric Properties of Yeast Cells, *J. Membrane Biol.*, **28**, 169 (1976).
42. T. Hanai and N. Koizumi: Numerical Estimation in a Theory of Interfacial Polarization Developed for Disperse Systems in High Concentrations, *Bull. Inst. Chem. Res., Kyoto Univ.*, **54**, 248 (1976).
43. K. Iwauchi, N. Koizumi, M. Kiyama, and Y. Bando: Magnetic Relaxation in Fe<sub>3</sub>O<sub>4</sub> and Ferrites, *ibid.*, **54**, 255 (1976).

#### Reviews

1. T. Hanai: Dielectric Properties of Disperse Systems, *Hyomen (Surface)*, **6**, 326, 405, 524, 601, 668 (1968), **7**, 194, 383, 509, 646, 786 (1969).\*

2. T. Hanai: Lipid Bimolecular Membranes as a Model for Plasma Membranes, *Farumashia*, **6**, 6 (1970).\*
3. T. Hanai: Underwater Black Films Consisting of Lipids—Their Physico-Chemical Properties and the Approaches to Biological Cell Membranes, *Kagaku to Kogyo (Chemistry and Chemical Industry)*, **24**, 188 (1971).\*
4. T. Hanai: Permeation of Reconstituted Membranes to Substances, *Clinic All-Round (Soogoo Rinshoo)*, **21**, 96 (1972).\*
5. T. Hanai: Bimolecular Lipid Membranes (Black Films), *J. Japan Oil Chemists' Soc.*, **21**, 289 (1972).\*
6. T. Hanai: Permeation of Artificial Thin Films to Ions, *J. Japan Medical Association*, **70**, 1372 (1973).\*
7. T. Hanai: Some Problems on Emulsions, I: A. Preparation of Emulsions and Their Physico-Chemical Properties, *Science of Cookery*, **6**, 173 (1973).\*
8. T. Hanai: Some Problems on Emulsions. II: B. Dielectric Properties of Emulsions, *ibid.*, **6**, 239 (1973).\*
9. T. Hanai: Some Problems on Emulsions, III: B. Dielectric Properties of Emulsions (continued), *ibid.*, **7**, 30 (1974).\*
10. T. Hanai: Some Problems on Emulsions, IV: C. Microcapsules, *ibid.*, **7**, 78 (1974).\*
11. T. Hanai: Some Problems on Emulsions V: D. Surface Films and Interfacial Films, *ibid.*, **7**, 141, (1974).\*
12. T. Hanai: Some Problems on Emulsion, VI: E. Underwater Black Lipid Membranes, *ibid.*, **7**, 198 (1974).\*
13. T. Hanai: Physico-Chemical Properties of Thin Lipid Membranes, *J. Japanese Chemistry (Kagaku no Ryoiki)*, *Supplement*, **103**, 25 (1974).\*
14. N. Koizumi: Physical Properties of Polar Molecules, *Kagakukyoiku*, **19**, 191 (1971).\*
15. N. Koizumi: Dielectric Properties of Fluorocarbon Polymers, 1 Basic Theories of Dielectric Properties, *Baruka Rebiyu (Valqua Reviews)*, **19**, no. 6, 9 (1975).\*
16. N. Koizumi: Dielectric Properties of Fluorocarbon Polymers, 2 Measurements of Dielectric Properties, *ibid.*, **19**, no. 7, 8 (1975).\*
17. N. Koizumi: Dielectric Properties of Fluorocarbon Polymers, 3 Measurements of Dielectric Properties, *ibid.*, **19**, no. 12, 1 (1975).\*

#### Books

1. T. Hanai: Experimental Methods for Lipid Bimolecular Membranes, in "Experimental Techniques for Biological Membranes", Section IV. 2.A, edited by T. Ohnishi, Nankoodoo, Tokyo and Kyoto (1967), p. 350.\*
2. T. Hanai: Electrical Properties of Emulsions, in "Emulsion Science" Chapter 5, edited by P. Sherman, Academic Press, London and New York (1968), p. 353.
3. T. Hanai: "Emarujyon no Kagaku", Translation of "Emulsion Science" edited by P. Sherman, Asakura Shoten, Tokyo (1971).\*
4. N. Koizumi: Dielectric Measurements, "Kobunshisokuteiho, Kozo To Bussei, Jo", Baifukan, Tokyo (1973), p. 478.\*
5. T. Hanai: Experiments on Black Membranes, and the Applications, Tanpakushitsu-Kakusan-Kouso (Protein, Nucleic Acid, and Enzyme), Supplement "Experiments on Biological Membranes", **B**, Kyouritsu Shuppan Co. Ltd., Tokyo (1974), p. 197.\*
6. N. Koizumi: Dielectric Constant and Loss, "Shinjikkenkagakujoza" No. 5, Kisogijutsu, **4**, Denki, Maruzen, Tokyo (1976), p. 265.\*